

Product name	Product	group	Production location
Caversham Mixture	Caversham Mixture L3		Lanklaar
The raw materials are excavated in Weichsel loam layers, th mainly consists of a silt-like fraction, suited ideally for the m surface covering, the desired colour is achieved.	e local loam of Aeolia anufacturing of hand	n origin dating fra form bricks. By u	om the Ice Age. This löss sing specific sand types for
	Colour		
yellow with white and dark shades			
	Format		
Moulding method Hand form			
DF: 215 x 102 x 65 mm	Between batches the	average size and colo	or may slightly differ.
Essential Cha	aracteristics - EN771-1		
CE		EN 771-1 - 0620-CPR-97884	
Dimensional tolerances	Т2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	>= 20 N/mm²	Tested to the b	bed face
Normalized Compressive strength	NPD	Tested to the b	bed face
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm²		
Bond Strength thin layer	0,30 N/mm²		
Reaction to fire	A1	Category	
Water absorption	<= 17% m/md		
Water vapour permeability	5/10		
Net dry density	1640 kg/m³ (D1)		
Gross dry density	1530 kg/m³ (D1)		
Thermal conductivity Lambda 50/50	<=0,55 W/m.K		
Durability against freeze thaw	F2		
Dangerous substances	NL-BSB	According to A	nnex ZA 3
Other	Characteristics		
Initial rate of water absorption - Non-coated Bricks	1,5 - 4.0 kg/m².min (IW3)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	0,5 - 1,5 kg/m².min (IW2)	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance	NPD	B 27-009	
Thermal conductivity Lambda 90/90	0,60 W/m.K		
Thermal conductivity Lambda Ui	0,644 W/m.K		_
Thermal conductivity Lambda Ue	1,27 W/m.K		

