

## **Technical Data Sheet**



## **High Performance Pre-Blended Bedding Mortar**

tuffbau's tuffbed is a high performance, naturally pure hydraulically bedding mortar, preblended with aggregate that needs only to have water added and be thoroughly mixed.

Bedding depths of between 15 mm to 50 mm may be placed in a single layer.

Greater depths may be accommodated by placing successive layers.

tuffbed is shrinkage compensated, reducing the risks of failure associated with building permanent stress into new pavement structures, the inevitable result of excessive shrinkage.

The elastic modulus of tuffbed is optimised to provide the correct supporting stiffness whilst continually absorbing the thermal and dynamic stresses inherent in all pavement structures.

tuffbed complies with or exceeds all performance requirements of BS7533-101:2021, table 9 ,Type 25 and Type 35 bedding mortars. When mixing, add approx 3-4 litres to each complete 25kg sack of tuffbed to achieve the recommended 150mm slump.

Storage life is twelve months in bone dry conditions (and product can remain fit for use if maintained in a dry powder form, with negligible deterioration of the all-natural ingredients) tuffbed is supplied as a bagged dry product packed in moisture resistant bags, to be mixed with water on site.

For an enhanced adhesion bond between the bedding layer and the underside of the paving elements, and the supporting layer beneath, the application of tuffbond priming mortar will ensure final compliance with the Britsh Standard.

## **Technical Specification**

Colour	Grey
Packaging	Bag
Packaging weight	25 kg
Bed depth range	15-50 mm
Typical water used	3-4 litres per 25 kg
Typical coverage	15 mm: 27 kg/m² 30 mm: 54 kg/m² 50 mm: 90 kg/m²
Packages per pallet	48
Pallet quantity	1 tonne
Working time	40 min at 10°C 30 min at 20°C
Working temperature	2-30°C
Compressive strength (20°C)	14 days: ~25 N/mm² 28 days: ~35 N/mm²
	~25 N/mm² 28 days:
(20°C)	~25 N/mm² 28 days: ~35 N/mm²
(20°C)  Modulus of elasticity	~25 N/mm² 28 days: ~35 N/mm²  14,000 - 18,000 N/mm²
(20°C)  Modulus of elasticity  Permeability	~25 N/mm² 28 days: ~35 N/mm²  14,000 - 18,000 N/mm² 2 x 10 - 4 m/s  24 months from manufacture
(20°C)  Modulus of elasticity  Permeability  Storage life	~25 N/mm² 28 days: ~35 N/mm²  14,000 - 18,000 N/mm² 2 x 10 · 4 m/s  24 months from manufacture date  M10 Q24
(20°C)  Modulus of elasticity  Permeability  Storage life  NBS sections	~25 N/mm² 28 days: ~35 N/mm²  14,000 - 18,000 N/mm² 2 x 10 -4 m/s  24 months from manufacture date  M10 Q24 Q25







1 Northwick Rd Canvey Island Essex SS8 0PU +44 203 598 9800 www.steintec.co.uk