

**Product Information**

|                        |                                 |
|------------------------|---------------------------------|
| Ibstock Code:          | A5232A                          |
| Type:                  | Stock                           |
| Facing Description:    | Sandcreased                     |
| Dry Brick Weight (kg): | 3kg                             |
| Pack Quantity:         | 408                             |
| Packaging (standard):  | Shrinkwrapped on pallets (wood) |
| Factory:               | Clerkenwell                     |

**Technical Specification (to BS EN 771-1)**

|   |            |
|---|------------|
| Brick Dimensions (L x W x H mm):                                    | 280x140x40 |
| Size Tolerances Mean & Range:                                       | T2 R2      |
| Configuration:  | Solid      |
| Voids (%):  | NPD        |
| Compressive Strength (N/mm <sup>2</sup> ):                          | 25         |
| Active Soluble Salts:   | S2         |
| Water Absorption (% weight):  | 9          |
| Durability:   | F2         |
| Gross Dry Density (Sound Insulation) (Kg/m <sup>3</sup> ):          | 2000       |
| Equivalent Thermal Conductivity "K" value 5% Exposed:               | 1.03       |
| Initial Rate of Absorption (Suction Rate) (Kg/m <sup>2</sup> /min): | NPD        |
| EAN:  | n/a        |