

Decorative coated aluminium trims for facades with CEDRAL. Different trims are available: e.g. external corner, internal corner, end profile, start profile, connection profile...

ARTICLE NUMBER: depending on type and colour

TECHNICAL DATA

Dimensions	see detailed drawings
Length	3.00 m
Thickness	1 mm
Colour	corresponding with Cedral colour
Substrate	Aluminium
International alloy name	EN AW 3105 or EN AW 3003
Coating process	Pre coating
Coating	Polyester
Gloss top coat	Matt
Coating thickness	22-28 microns
Pencil hardness (ECCA T4)	Min F
UV-resistance	Category 3, index 2 (EN 1396, part C.6)
Corrosion resistance	Category 3, index 3 (EN 1396, part C.6)
Protection foil	Yes

PACKAGING

Packaging: bundle of 5 pieces

PROCESSING

Consult the application guidelines for CEDRAL

MAINTENANCE

To maintain optimum appearance and lifetime of the coated surface, it is recommended that washing is done every six months. Surfaces which are exposed to more contaminated areas, like coastal- and industrial areas, are recommended to be washed more often. Washing should be done with water containing very mild soap, like car shampoo. Rinse thoroughly with clean water.



Cedral external symmetrical corner	Cedral external asymmetrical corner	Cedral internal corner
Connection profile	Cedral end profile	Cedral start profile
Cedral Click external corner	Cedral Click internal corner	Cedral Click lintel profile

Disclaimer

The information in this Material Information Sheet is correct at time issuing. However, due to our committed program of continuous material and system development we reserve the right to amend or alter the information contained therein without prior notice. Please contact your local Etex Facade Sales Organization to ensure you have the most current version.

All information contained in this document is copyrighted ©.

All figures contained in this document are illustrations and should not be used as construction drawings.

This information is supplied in good faith and no liability can be accepted for any loss or damage resulting from its use.