

H40 Gel

Multipurpose Gel-Adhesive, structural, flexible, thixotropic & fluid. For ceramic, porcelain and natural stone of all types and formats.



1. High adhesion and deformability
2. Excellent workability
3. Ideal for facades, swimming pools and heavy traffic environments
4. Suitable for residential, commercial and infrastructure projects

Rating 2

W G

- × × Regional Mineral ≥ 60%
- × × Recycled Mineral ≥ 30%
- × × CO₂ ≤ 250 g/kg
- ✓ ✓ VOC Very Low Emission
- ✓ ✓ Recyclable



Areas of application

→ Intended use:

Substrates:

- existing tiles
- waterproofing products
- cement-based screeds
- concrete substrates
- plasterboard
- fibro-cement slabs
- brick/blockwork
- lime and cement-based plasters/renders
- thermal insulation panelling systems
- insulating panels
- impact noise insulation sheets

Materials:

- porcelain tiles
- laminated stoneware
- low thickness slabs
- ceramic tiles
- large size
- 300x150 cm slabs
- marble - natural stone
- recomposed materials
- glass mosaics
- glass tiles
- thermal and acoustic insulation
- terracotta - klinker

Uses:

- adhesive and finishing
- for floors and walls
- for internal use - external
- overlaying
- terraces and balconies
- facades
- swimming pools and fountains
- saunas and spa
- domestic
- commercial
- industrial

Instructions for use

→ Preparation of the substrate

All surfaces must be dimensionally stable according to IS 1443-1972, level, cured, undamaged, compact, rigid, resistant, dry and free from any debonding agents and from damp rising.

It is good practice to dampen highly absorbent concrete substrates or apply a coat of Primer A Eco.

→ Preparation

Mixing water on-site

For low thickness laying and full wettability:

≈ 5 - 6.2 litres per 20 kg bag

The amount of water indicated on the packaging is indicative. It is possible to obtain mixtures with consistency of variable thixotropy according to the application to be made.

→ Application

To guarantee structural adhesion it is necessary to apply a layer of adhesive sufficient to cover the entire back of the coating material.

Large, rectangular sizes with sides > 60 cm and low thickness sheets may require adhesive to be applied directly to the back of the material.

Check samples to make sure the adhesive has been transferred to the back of the material.

Create elastic expansion joints:

- ≈ 10 m² in external applications,

- ≈ 25 m² in internal applications,

- every 8 metres in long, narrow applications.

Respect all structural, fractionizing and perimeter joints present in the substrates.

Special notes

→ Pre-treatment of special substrates

Gypsum and anhydrite (internal use only):
Primer A Eco

As treating special surfaces is difficult to classify in a standard manner, it is always advisable to contact Kerakoll Global Service and/or request a site inspection by a GreenBuilding Consultant. In any case it is essential to carefully read the technical data sheet on how to use the indicated primers properly.

→ Materials and special substrates

Marble–natural stones and Recomposed materials: materials that are known to be subject to deformation or staining due to water absorption require a quick-setting or reactive adhesive.

Marble and natural stone in general may have characteristics that vary even with reference to materials of the same chemical and physical nature. For this reason it is essential you consult Kerakoll Global Service to request specific indications or to carry out a test on a sample of the material.

In the absence of specific indications from the manufacturer, natural stone slabs with reinforcement layers, in the form of resin coating, polymer mesh, matting, etc. or treatments (for example damp courses, etc.) applied on the laying surface must be tested in advance to ensure they are compatible with the adhesive. Check for the presence of any really consistent traces of rock dust created during cutting, and remove them if found.

Waterproofing products: adherent and floating polymer sheets, liquid bitumen and tar-based sheets or membranes require application of a laying screed on top.

→ Special applications

Facades: the surface should guarantee a cohesive tensile strength of $\geq 1.0 \text{ N/mm}^2$.

The need to call for suitable mechanical safety anchoring must be evaluated by the designer for coverings with $> 30 \text{ cm}$ side.

For coverings with $> 60 \text{ cm}$, add to the mixing water a percentage of Top Latex Eco to assess the function of the thermo-dynamic strain provided by the structure.

Always apply a layer of adhesive directly on the back of the tile/stone.

Certificates and marks



Technical Data compliant with Kerakoll Quality Standard

Shelf life	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	20 kg bags	
Adhesive thickness	up to 15 mm	
Temperature of the air, substrates and materials	from +5 °C to +35 °C	
Pot life at +23 °C		
- Grey	≈ 6 hrs	
- White	≈ 4 hrs	
Pot life at +35 °C (BIII tile):		
- Grey	≈ 3 hrs	
- White	≈ 3 hrs	
Open time at +27 °C (BIII tile)		
- Grey	≥ 35 min.	EN 12004-2
- White	≥ 35 min.	EN 12004-2
Correction time at +27 °C (BIII tile)	≥ 60 min.	EN 12004-2
Foot traffic/grouting of joints at +23 °C (BIa tile):		
- Grey	≈ 20 hrs	
- White	≈ 20 hrs	
Foot traffic/grouting of joints at +35 °C (BIa tile):		
- Grey	≈ 12 hrs	
- White	≈ 12 hrs	
Grouting in walls at +23 °C (BIa tile)		
- Grey	≈ 18 hrs	
- White	≈ 18 hrs	
Grouting in walls at +35 °C (BIa tile):		
- Grey	≈ 8 hrs	
- White	≈ 8 hrs	
Ready for use at +23 °C / +35 °C (BIa tile):		
- foot traffic	≈ 3 – 2 days	
- heavy traffic	≈ 4 – 3 days	
- swimming pools (+23 °C)	≈ 14 days	
Coverage per mm thickness:		
- Grey	≈ 1.3 kg/m ²	
- White	≈ 1.2 kg/m ²	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the site, i.e. temperature, ventilation and absorbency level of the surface and of the materials fixed.

Performance**VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

Conformity	EC 1 plus GEV-Emicode	GEV certified 14613/11.01.02
------------	-----------------------	---------------------------------

HIGH-TECH

Tensile adhesion strength (dry condition)	$\geq 2.5 \text{ N/mm}^2$	IS 15477:2019
---	---------------------------	---------------

Tensile adhesion strength (wet condition)	$\geq 1 \text{ N/mm}^2$	IS 15477:2019
---	-------------------------	---------------

Shear adhesion strength (dry condition)	$\geq 1,5 \text{ N/mm}^2$	IS 15477:2019
---	---------------------------	---------------

Shear adhesion strength (heat ageing condition)	$\geq 1 \text{ N/mm}^2$	IS 15477:2019
---	-------------------------	---------------

Shear adhesion strength (wet condition)	$\geq 1 \text{ N/mm}^2$	IS 15477:2019
---	-------------------------	---------------

Durability test:

- adhesion after heat ageing	$\geq 1 \text{ N/mm}^2$	EN 12004-2
------------------------------	-------------------------	------------

- adhesion after water immersion	$\geq 1 \text{ N/mm}^2$	EN 12004-2
----------------------------------	-------------------------	------------

- adhesion after freeze-thaw cycles	$\geq 1 \text{ N/mm}^2$	EN 12004-2
-------------------------------------	-------------------------	------------

- adhesion after straining cycles	$\geq 1 \text{ N/mm}^2$	SAS Technology
-----------------------------------	-------------------------	----------------

Vertical slip	$\leq 0.5 \text{ mm}$	EN 12004-2
---------------	-----------------------	------------

Transversal deformation	$\geq 2.5 \text{ mm}$	EN 12004-2
-------------------------	-----------------------	------------

Working temperature	from $-40 \text{ }^\circ\text{C}$ to $+90 \text{ }^\circ\text{C}$	
---------------------	---	--

Values taken at $+23 \text{ }^\circ\text{C}$, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the site.

Warning

- Product for professional use
- abide by any standards and national regulations
- do not use the adhesive to correct substrate irregularities greater than 15 mm
- protect from direct rainfall for at least 24 hrs
- the temperature, ventilation and absorption of the substrate and covering materials, may vary the adhesive workability and setting times
- use the right size of notched trowel for the format of the tile or slab
- guarantee a full-bed in all external laying operations
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll India Helpline (Toll Free) 1800-200-6550 – info@kerakollindia.com

The Rating classifications refer to the GreenBuilding Rating Manual 2013. This information was last updated in July 2024 (ref. GBR Data Report - 06.24); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.