

ACCROLOR 2

PASTE MICRO BASE COAT



IMPROVES THE ADHERENCE OF RENDERS ON SMOOTH CONCRETE

- ✓ Reduces render bug holes
- ✓ Quick drying: can be rendered the same day
- ✓ Base coat suitable for cellular concrete blocks

PROJECT SOLUTION TO BE CHECKED OUT P. 114-115

Exterior walls



PRODUCT INFORMATION

Consumption

- On smooth concrete: 100 g/m² of pure product (i.e. 150 g/m² of diluted product).
- On cellular concrete: 300 g/m² of pure product (i.e. 450 g/m² of diluted product).

Storage

1 year in its unopened original packing and stored away from frost and high temperatures.

Packaging

15 kg tub

SPECIFICATIONS AND PERFORMANCES

Appearance: yellow liquid

Composition: synthetic resin emulsion, fine fillers, additives

Density: 1.5

pH: 8

FIELD OF USE

Purpose

Reinforces the adherence of hydraulic renders

Authorised bases

- Concrete, in particular smooth or non-absorbent concrete.
- Cellular concrete.

Unauthorised bases

- Wet or frozen bases.

APPLICATION

Application conditions

- Application temperature: +5°C to +30°C.
- The base must not be frozen or overheated.
- Do not apply when rain or freezing temperatures are imminent.

Precautions for use

In order to protect your health and the environment, and for the safe use of this product, follow the precautionary advice that is featured on the packing label. You can find the safety instructions for this product on the Safety Data Sheet (SDS) available on quickfds.com.

Base preparation

- The base must be clean, sound and free of any non-adhesive parts or areas that could prevent adhesion (for example: release oil, drying products, etc.).
- It must comply with the relevant CPTs and DTUS.
- Base with plant pollution (mosses, algae, lichens, fungi): Treat using an anticryptogamic solution.

Product preparation

- Add 5 L of water directly into the tub of ACCROLOR 2.
- Mix carefully using a low speed electric mixer.

Application

WORKABLE TIME AT +20°C

Minimum time before covering	45 min (the product must be dry to the touch)
Maximum time before covering	72 hours (after this period, apply a new layer)

- Apply ACCROLOR 2 using a brush or roller, properly impregnating the base and avoiding excess.
- Wait for ACCROLOR 2 to dry completely before applying the hydraulic render (45 min minimum at +20°C), but not more than 72 h. Beyond this time, apply a new layer of ACCROLOR 2.
- Clean the tools with water while the product is fresh.

The purpose of the information provided on this technical sheet is to inform of the product's current properties. It cannot, under any circumstances, be considered as a guarantee nor as engaging our liability due to varying use and application techniques and materials used. We strongly recommend preliminary testing. When this document was drawn up, all indications were based on current technical development data and our experience. The most recent version is available on www.vicat.fr.