

TECHNICAL DATASHEET - Vent3 Light – Breathable Membrane

Description

Vent3 Light is a lightweight triple layer fabric, high performance breather membrane, made from high tensile spun bonded polypropylene layers, around a micro-porous polypropylene film. Designed for use as a universal breather membrane for roofs and walls boasting superior moisture vapour permeability. Vent3 Light has a printed (dark grey) upper surface with preprinted marking lines and a white under-face. The high vapour permeability and waterproof properties of the membrane, combined with excellent tensile/tear strength, make Vent3 Light an ideal product for use in all pitched roof applications. It will allow the escape of water vapour from within the roof structure whilst protecting against wind driven rain, snow and dust which may penetrate the main roof waterproofing, providing a permanent quality breather underlay, which will last the life of the roof construction.

Benefits

- BBA certified
- Independently tested and BS 5534:2014+A2:2018 compliant
- Conforms with BS 5250 guidelines
- Meet NHBC guidance for underlays in pitched roof applications
- Clean and easy to use
- Excellent tensile and tear strength
- Waterproof properties
- Long term durability
- UV Stable (3 months exposure)
- Warm and Cold Roof Application



PRODUCT DATA

Product	Weight	Flame Retardancy	Sizes	Colour	Nail Tear Strength	Tensile Strength	Elongation %	Water Vapour Transmission (sd) m	Water Vapour Resistance MNs/G	BS 5534 Zones Compliance	UV resistance	Roll weight Kg	Pallet quantity (50m rolls)
Vent 3 Light	95gsm	Class F EN 13501-1	1m & 1.5m x 15m, 25m, 45, & 50m	Dark Grey / White	83 N 93 N	245N/50mm 145N/50mm	60 MD 96 XD	W1	<0.02	BS 5534:2014 +A1:2018	3 months	4.75 7	56 56

BS 5534:2014+A2:2018 Wind Uplift

Each individual Vent3® underlay product has the batten gauge & zonal application for wind uplift printed on this packaging. The manufacturer's declared values are available from the Cromar website and the BBA certificate. The Vent3® underlays may be used at any batten gauge in all wind zones when laid over nominally air-tight sheet sarking for example OSB, plywood, chipboard and insulation for warm-roof design. They may also be used in applications where slates are nailed directly onto sarking boards. Sarking boards, such as square-edged butt jointed planks, are not considered to be air-tight and the underlay is treated as unsupported.

	345mm Batted Lap	250mm Batted Lap	345mm Taped Lap	250mm Taped Lap
Vent3 Light	1	1 - 3	1 - 4	1 - 5



Application

Vent3 Light must be installed in accordance with the relevant sections of BS 5534:2014+A2:2018 and Cromar's fixing instructions.

Vent3 Light is designed as a secondary barrier to wind driven rain and snow, it should not be considered a primary waterproofing layer. Whilst the product is UV stable for up to 3 months exposure, good roofing practice dictates that the primary waterproofing finish (e.g. tiles, slates etc.) be applied as soon as practically possible.

Under slating membranes should not be considered as temporary weatherproof protection for occupied buildings or where internal fitting out is taking place. Additional protection should be afforded in these circumstances.

Vent3 Light should be unrolled across the roof, starting at the eaves and working up the roof, it is laid light grey (printed) side up. With normal slates and tiles the Vent3 Light membrane can be installed draped 10mm to 15mm into the void between the rafters, it can then be secured with the tiling battens. This will leave sufficient space between the Vent3 Light and the tiles/slates for drainage and ventilation. Vent3 Light when installed as a fully supported system, is laid over the support and secured with counter battens, alternatively the membrane can be installed over counter battens and fixed at 200mm centres using corrosion resistant straps or galvanised clout nails. Tiling battens are fixed to the counter battens leaving a minimum airspace of 25mm between the roof sheet underlay and the tiles for drainage and ventilation.

In unventilated roof systems vapour control measures are required below the insulation layer to restrict the flow of moist air from within the inhabited building into the roof space. Additionally, the building below should be ventilated in accordance with the Building Regulations with water tanks sealed.

Abutment flashing should be wedged into a mortar joint 25mm deep and at least 150mm above the level of the slates or tiles. Vent3 Light underlay should be turned up behind the flashing at least 100mm to prevent rain and snow being blown into the roof-space. Lap joints in the membrane should be generally in accordance with the table set out below. 600mm reinforcing strips should be fixed at hips, ridges and valleys.

At the eaves Cromar felt support trays should be installed to prevent ponding behind the fascia. The Vent3 should be laid over the support tray stopping short of the roof tile tails to prevent UV degradation of the underlay.

Notes

1. As with all breather membranes of this type, contact with solvents or wet timber preservatives can cause localised water penetration to occur, prior to the main weatherproofing being installed.
2. In accordance with BS 5534:2014+A2:2018 where a roof underlay or breather membrane is to be laid over open rafters, a nominal drape of 10mm between the rafters is desirable to guide any rainwater penetrating the main roof finish away from the rafters to the drainage point. (The membrane must not be pulled tight against the underside of the tiling battens.)
3. Vent3 should never be considered as being a total protection against wind-blown rain and high winds.

Limitations

- It is the user's responsibility to ensure suitability for use. Safety Data available on request.
- Read the label carefully for essential health and safety information prior to use.
- Health & Safety Care should always be taken when working at height. The safety of all working in construction is critical, above and below. Cromar Vent3 breather membranes should not be used as part of a fall arrest system.
- Exposure – Vent3 breather membranes may remain unprotected for up to 3 months, but recommended practice is to install tiles or slates as soon as possible, to minimise risk of water ingress through unsealed overlaps, edges and nail holes after any rain, in line with the guidance from the NHBC and the BBA we recommend the felt be covered in just a few days.

Further Information:

In the event of further queries or problems concerning the use of this product, please contact the address below, e-mail sales@cromar.uk.com.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.