


## High Performance Polyester Reinforced Torch-on Waterproofing



Plain

Green

Charcoal

Chestertorch is a multi-layered bituminised waterproof system designed for use on various types of flat roofing projects including new build and refurbishments, cold roofs and warm roofs using vapour control layers with insulation. This range of membranes feature a polyester core which is saturated and coated in modified bitumen and the upper surface is finished with a choice of either light sand or slate mineral.

When incorporated in a suitably designed and installed multi-layer system, maintained in accordance with BS 8217:2005 - Reinforced bitumen membranes for roofing, Chestertorch membranes may be expected to last in excess of 10 years.

### Product Details

Product Code	Roll Length	Roll Width	Finish	Pallet Quantity
P825	8m	1m	Plain	30 rolls
P826	8m	1m	Green Mineral	30 rolls
P829	8m	1m	Charcoal Mineral	30 rolls

### Key Features & Benefits:

- Polyester reinforced
- Strength and durability
- Modified bitumen
- Cost-effective system

### Suitability

Chestertorch Plain has a sand surfaced membrane and may be used both as an under layer and a cap sheet. Where used as a cap sheet, suitable protection from ultraviolet light is required in the form of either premium grade solar reflective paint or suitable walkway type tiles which are suitable for use

over bituminous system. Chestertorch polyester cap sheets can be relied upon to react in unison when combined in multi-layer built up roofing systems. Such combinations are readily applicable to roofs with high insulation values where considerable thermal movement is likely to occur.

### Installation Guidelines

This product should be installed in accordance with manufacturer recommendations and all relevant national standards and codes of practice, including BS 8217:2005 – the code of practice for reinforced bitumen membranes for roofing. **Please be advised that this product should not be installed in temperatures below 5°C.**

### Mineral Surface Protection

The upper surface of certain Chestertorch membranes is protected using mineral granules, which are sourced from natural quarrying. The colours of the minerals therefore can sometimes vary depending on seam depths and extraction positions within the quarry. However, after the effects of the weathering and ageing, any variations will become less visible.

## Performance and Key Properties

Characteristic	Test Method	Result	Tolerance
Roll Length	BS EN 1848-1	8m	+/- 150mm
Roll Width	BS EN 1848-1	1m	+/- 1.5%
Roll Weight	BS EN 1849-1	32kg	+/- 5%
Straightness	BS EN 1848-1	PASS	
Visible Defect	BS EN 1850-1	PASS	
Adhesion of Granules	BS EN 12039	2%	<20%
Watertightness	EN 1928:2000 Method A	PASS	
Resistance to tearing	BS EN 12310-1		
Longitudinal		134 N/50mm	>100 N
Transverse		171 N/50mm	>100 N
Flexibility at low temperature	BS EN 1109	-5°C	+/- 2%
Tensile Properties	BS EN 12311-1		
Longitudinal		762 N/50mm	>350 N
Transverse		501 N/50mm	>250 N
Tensile elongation	BS EN 12311-1		
Longitudinal		41%	>20%
Transverse		45%	>20%

### Maintenance and Repair

Routine inspection, cleaning and maintenance of the roof membranes should be based on the recommendation in BS 8217:2005. Should it be damaged either during construction or at later date, then the repairs should be made using the same materials so that the performance of the built-up membranes is retained.

### Standards

Manufactured in accordance with BS EN 13707:2004+A2:2009 - Flexible sheets for waterproofing. Reinforced bitumen sheets for roof waterproofing.

### Handling and Storage

The material should be stored vertically on a firm flat surface, and transported stood on end to avoid damage.

### Certification

UKCA certified & CE Marked to EN 13707:2004+A2:2009.

CE Certificate Number: 0086-CPR-595938.

UKCA Certificate Number: 0086 CPR 753192.

### Health and Safety

Health and Safety should be observed at all times in accordance with HSE and industry guidance. Specific Risk Assessments and Method Statements should be produced by contractors where necessary to ensure Working at Heights, Fire Safety and Manual Handling rules are compliant with current law and regulations. Health and safety data sheets are available for all materials on request from Chesterfelt.

### Quality Assurance

Chestertorch membranes are manufactured in accordance with BS EN ISO 9001:2015 - Quality Management Systems (QMS).

### Associated Products

Chestertorch system membranes.



Cert No.  
0086-CPR-595938



Chesterfelt Ltd Foxwood Way, Sheepbridge, Chesterfield, Derbyshire, S41 9RA  
Telephone: 01246 268000 Email: technical@chesterfelt.co.uk Web: chesterfelt.co.uk



All rights are reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work activities presented in this document is not permitted. Extreme caution was observed when putting together the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for improvement suggestions and details of errors pointed out.