

FRAMESHIELD 100

user guide

FRAMESHIELD 100 DETAILS

General

Frameshield 100 is a spunbonded polypropylene material developed primarily as a breather membrane for use in timber frame wall and light steel frame applications.

Applied in the factory during manufacture or on site, Frameshield 100, affords effective protection of timber frames during construction against wind-driven rain, snow and dust. Once completed, the high water vapour permeability of Frameshield 100 allows the controlled escape of vapour from within the timber frame whilst restricting the ingress of rain and moisture.

Frameshield 100 conforms to the Construction Products Regulation (EU Regulation No. 305/2011), Underlay for walls (Annex ZA of EN 13859-2) and is manufactured under control of an ISO 9001 quality management system. Its vapour resistance factor of 0.03MNs/g is less than the maximum permitted in NHBC requirements. Used in accordance with this NHBC Practice Note, Frameshield 100 provides a superior quality permanent wall breather membrane.

Exclusively developed and produced for the A. Proctor Group to carefully determined specifications by Britain's only spunbonded fabric manufacturer, Don & Low Limited Nonwovens, Forfar, Scotland.



Wall Breather Membrane

Frameshield 100 is produced by the continuous extrusion of polypropylene fibres which are then spun and bonded together with a combination of heat and pressure.

Installed in accordance with the NHBC standards, Frameshield 100 will comply with all current UK Building Regulations.

PRODUCT CHARACTERISTICS

| | |
|--|---------------------------|
| Mass per unit area (EN 1849-2) | 100g/m ² |
| Reaction to Fire (EN 13501-1) | Class E |
| Water vapour resistance Sd (EN 12572) | 0.006m |
| Water penetration (EN 1928) | |
| Before ageing: | Class W2 |
| After ageing: | Class W2 |
| Tensile strength (EN 12311-1) | |
| Before ageing: | MD 240N CD 180N |
| After ageing: | MD 200N CD 150 N |
| Elongation (EN 12311-1) | |
| Before ageing: | MD 85% CD 100% |
| After ageing: | MD 45% CD 60% |
| Tear resistance (EN 12310-1) | MD 135N CD 145N |
| Flexibility at low temperature (EN 1109) | No cracking at minus 60°C |

Application Details

Supplied in roll form, Frameshield 100 should be fixed to frames with austenitic stainless steel nails or staples at centres not more than 500mm. On areas where sheets are required to be lapped, the following dimensions must be adhered to:

| | | |
|-----------------|---|---------------------|
| Vertical Laps | — | not less than 150mm |
| Horizontal laps | — | not less than 100mm |

Ensure integrity of Frameshield 100 by overlapping upper layers over lower layers and staggering vertical joints. Protect timber at wall plate level and mark stud positions for wall fixings. Once applied to the wall, Frameshield 100 should be covered within 3 months.

Application Procedure

Frameshield 100 must be installed in accordance with the A. Proctor Group's instructions.



Don & Low
MEMBER OF THRACER GROUP

FRAMESHIELD CHARACTERISTICS

| | |
|-------------|-----------------------------|
| Thickness | 0.5mm |
| Weight | 100g/m ² |
| Roll Length | 100m |
| Roll Width | 2.7, 1.5 (black) or 1.4m |
| Colour | Green/Grey Others Available |

The product is manufactured under an ISO 9001 compliant system with quality control checks carried out on the finished product.

Quality control checks on the finished product include:

- Weight
- Tensile strength and elongation
- Tear
- Water penetration

The contents of this installation guide are provided by A. Proctor Group Limited (APG) in good faith for general information purposes only. The statements and data contained in this guide are not specific technical recommendations as to any particular design or application. APG give no warranty and accept no liability for its contents and the ultimate determination as to product suitability is the sole responsibility of the installer or end user. APG strongly recommends following the installation guidelines and the relevant Codes of Practice which are correct at the time of publication and results may vary depending on the particular design and/or application.



Insert Code
002
July 2021

TECHNICAL ADVICE

The A. Proctor Group has a dedicated Technical Department which can deal with installation details, view drawings for approval and give specialist advice on the correct use of the A. Proctor Group products.

Telephone: +44 (0) 1250 872261
Facsimile: +44 (0) 1250 872727
email: contact@proctorgroup.com
www.proctorgroup.com

ACOUSTIC SOLUTIONS
CONDENSATION CONTROL
THERMAL SOLUTIONS
GROUND GAS PROTECTION