

RUST-OLEUM®

INDUSTRIAL



HARD HAT® TOPCOAT HEAT RESISTANT

Heat resistant coating up to 750°C



- For continuous temperatures up to 650°C
- For peak temperatures up to 750°C
- For on bare metal or slightly rusted surfaces
- Ideal for engines, heat cannons, pipes, vents, etc.
- To handle after 3 hours (at 20°C)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® TOPCOAT HEAT RESISTANT

DESCRIPTION

Hard Hat® 1015 and 1078 are Heat Resistant Coatings based on a silicone modified alkyd resin.

RECOMMENDED USE

HARD HAT® Heat Resistant Coating can be applied on new, bright or shot-blasted steel or well pre-treated coated surfaces such as barbecues, boiler fittings, hot air cannons, exhausts, etc.

HARD HAT® Heat Resistant Coating is intended for small maintenance jobs and repairs.

HARD HAT® Heat Resistant Coating provides protection up to a dry heat of 750°C (short-term peak load) for applications indoors or in a sheltered outdoor environment.

TECHNICAL DATA

| | |
|------------------|--|
| Gloss Level: | Matt |
| Corrosion Class: | N / A |
| Heat Resistance: | Standard 600°C (dry heat) / Short term peak 750°C (dry heat) |

DRY TIMES BY 20° C/RH 50%

| | |
|----------------|--|
| Touch dry: | 2 hours |
| Dry to handle: | 8 hours |
| Dry to recoat: | 24 hours |
| Fully cured: | Allow the product to dry for 3 hours at room temperature and then heat to 150°C in stages of max. 50°C/hour. Allow to cool for 24 hours. The product is now fully cured. |

RECOMMENDED WET FILM THICKNESS

85 µm

RECOMMENDED DRY FILM THICKNESS

35-40 µm

THEORETICAL CONSUMPTION

10-12 m² per litre at 35 - 40 µm dry

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Only apply if the air and surface temperatures are between 5 and 35°C and the relative humidity is less than 85%.

The temperature of the coated surface must be at least 3°C above the dew point.

APPLICATION & THINNING: BRUSH

No thinning

APPLICATION & THINNING: ROLLER

No thinning. Use shorthaired polyamide (perlon 8 - 12 mm) rollers

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Dilute up to 10 to 15% volume RUST-OLEUM Thinner 7301

CLEANING OF EQUIPMENT / SPILLS

With RUST-OLEUM thinners 7301.

REMARKS

RUST-OLEUM Heat resistant coating 1015 and 1078 are self-priming and should not be applied on primers or coatings, which are not heat resistant.

SAFETY DATA

| | |
|---------------------------|--|
| VOC level: | 1015: 458 g/l max / 1078: 416 g/l max |
| VOC ready mix: | 1015: 458 g/l max / 1078: 416 g/l max |
| VOC category: | A/i |
| VOC limit: | 500 g/l |
| Remarks regarding safety: | Consult Safety Data Sheet and Safety information printed on the can. |

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the user's responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu