

March 2018

**PRODUCT DATA SHEET**

<b>Product</b>	<b>Boiled Linseed Oil</b>
<b>Type</b>	Modified so as to increase the rate of drying and hardness of the film
<b>Intended Use</b>	Ideal for oiling bare wood, adding to paint and softening Metal Glazing Putty. Not suitable for oiling furniture or wooden floors. For furniture use <b>Rustin's Danish Oil</b> or <b>Teak Oil</b> . For floors use <b>Rustin's Floor Oil</b> .
<b>Special Features</b>	Boiled to speed up drying time.
<b>Preparation</b>	Ensure surface to be oiled is clean and dry.
<b>Application</b>	Apply with a rag or brush and wipe off excess with a dry rag or cloth.
<b>Coats</b>	Apply 2 – 3 coats initially.
<b>Drying Time</b>	16- 24 hours. Dependant on temperature, humidity and film thickness.
<b>Re-coating Time</b>	Recoat once oil has dried.
<b>Application Temp.</b>	Ideally 15-25°C. Do not use below 10°C, or in conditions of high humidity.
<b>Coverage</b>	11- 14 square metres per litre per coat, depending on the absorbency of the wood
<b>Maintenance</b>	Re-oil periodically. Surfaces treated with Boiled Oil can be cleaned with a damp cloth.
<b>Compatibility</b>	Compatible with most oil based products. Refer to manufacturer before mixing with other products.
<b>Settlement</b>	Shake well before use.
<b>Shelf-life/Storage</b>	The shelf life of the product in an airtight container is a considerable period of time. It is preferable to store the product in a cool place. It is important to replace the lid and ensure an airtight seal.
<b>Hazards</b>	Low Hazard. See Health & Safety data sheets. <b>Important:</b> Rags used for oiling should be laid out flat to dry; otherwise they may catch fire due to spontaneous combustion.
<b>Clean-Up</b>	Clean brushes with white spirit or <b>Rustin's Brush Cleaner</b> . Brushes that have hardened may be cleaned with <b>Rustin's Brush Restorer</b> .
<b>Sizes</b>	125ml 250ml 500ml 2lit 4lit 25lit