

## Visqueen DPM

### Features & benefits

- BBA certified - third party accreditation
- Manufactured using a minimum 85% recycled polyethylene
- Range of thicknesses available

### Product description

Visqueen DPM is manufactured from a minimum 85% recycled polyethylene. The product is black in colour and available in three thicknesses: 0.25mm (4m x 25m) , 0.3mm (4m x 25m) and 0.5mm (4m x 12.5m). All rolls are supplied multi folded.

Please note Visqueen DPM is NOT accredited for radon applications. Please use either Visqueen Ultimate RadonBlok 600 or Visqueen Radon R400 Membrane.

### Approvals and standards

- Third party accreditation (BBA 94/3009)
- UKCA UKNI CE to EN 13967:2017
- Visqueen certified with Quality Management System ISO 9001:2015
- Visqueen certified with Occupational Health and Safety System ISO 45001:2018
- Visqueen certified with Environmental Management System ISO 14001:2015

### Usage

Visqueen DPM is suitable for use in ground floor constructions, positioned above or below the structural floor, to protect buildings against moisture from the ground.

The product is not intended for use where there is a risk of hydrostatic pressure or accredited for radon applications. Suitability for use of 0.25mm (1000 gauge) Visqueen DPM should be confirmed and approved by all stakeholders prior to use.

### System components

- VisqueenPro Double Sided Jointing Tape, 50mm x 10m
- VisqueenPro Detailing Strip, 300mm x 10m, 500mm x 10m
- VisqueenPro Single Sided Tape, 75mm x 25m
- Visqueen Top Hat Units
- Visqueen TreadGUARD 1500, 1m x 2m
- Visqueen TreadGUARD 300, 2m x 75m

### Storage and handling

Visqueen DPM should be stored horizontally, under cover in its original packaging.

Care should be taken when handling the product in line with current manual handling regulations.

### Preparation

Visqueen DPM should be installed on a smooth continuous surface e.g. grouted beam and block floor, a compacted blinding layer e.g. 50mm thick sand blinding, or smooth concrete blinding. The substrate should be free from irregularities such as voids or protrusions.

The membrane can be cut with a sharp retractable safety knife or robust scissors.

### Installation

Visqueen DPM should be loose laid on the substrate. The membrane should be clean and dry at the time of jointing. It should be overlapped by a minimum of 150mm, bonded with Visqueen Pro Double Sided Jointing Tape and sealed with Visqueen Pro Single Sided Tape.

Damp proofing seals should be formed around all service entry points. Visqueen Preformed Top Hat Units are available for sealing service entry pipe junctions. The base of the top hat and the upstand should be bonded using Visqueen Pro Double Sided Jointing Tape and sealed with Visqueen Pro Single Sided Tape. The upstand should be secured with the supplied jubilee clip. Alternatively Visqueen Pro Detailing Strip can be used to seal service entry pipe detailing.

Forming an effective barrier to damp with the membrane may give rise to complex three-dimensional detailing. To simplify complex or awkward junctions e.g. internal and external corners Visqueen Preformed units are available. Alternatively Visqueen Pro Detailing Strip can be used to seal awkward junctions.

If the membrane is punctured or perforated a patch of the same material should be lapped at least 150mm beyond the limits of the puncture and bonded with Visqueen Pro Double Sided Jointing Tape and sealed with Visqueen Pro

## Visqueen DPM

Single Sided Tape. Alternatively a patch can be formed using Visqueen Pro Detailing Strip and lapped at least 150mm beyond the extents of the puncture.

The membrane should be covered immediately after installation to prevent damage from following trades, ultraviolet light, etc. Care should be taken to ensure that the membrane is not punctured, stretched or displaced when applying the final floor covering.

When reinforced concrete is to be laid over the membrane the wire reinforcements and spacers must be prevented from puncturing the membrane. Where there is a potential risk of damage, the membrane should be covered with Visqueen TreadGuard protection, screed, or other approved protection material before positioning the reinforcement.

In areas where high levels of settlement are anticipated, Visqueen Pre Applied Membrane should be considered.

### Usable temperature range

It is recommended that Visqueen DPM and all associated system components should not be installed below 5°C.

### Additional information

To assist build sequencing, Visqueen Zedex CPT High Performance DPC is available for damp protection through masonry wall constructions.

Please note DPM is NOT accredited for radon applications. Please use either Visqueen Ultimate RadonBlok600 or Visqueen Radon R400 Membrane. For additional detailing information or for further guidance on the selection of the most appropriate thickness of membrane, contact Visqueen Technical Services +44 (0) 333 202 6800.

The information in this datasheet was correct at the time of publication. It is the user's responsibility to obtain the latest version of the datasheet as it is updated on a regular basis. The information contained in the latest datasheet supersedes all previously published editions.

Property	Test method	Units	Compliance criteria	0.25mm	0.3mm	0.5mm
Dimensions				4mx25m	4mx25m	4mx12.5m
Straightness	BS EN 1848-2	-	Pass/Fail	Pass	Pass	Pass
Tensile strength - MD	BS EN 12311	N/ mm <sup>2</sup>	>MLV	13	13	15
Tensile strength - TD	BS EN 12311	N/ mm <sup>2</sup>	>MLV	13	13	15
Tensile elongation - MD	BS EN 12311	%	>MLV	400	400	400
Tensile elongation - TD	BS EN 12311	%	>MLV	400	400	400
Joint strength	BS EN 12317-2	N	>MLV	136	169	256
Watertightness at 2kPa for 24 hours	BS EN 1928	-	Pass/Fail	Pass	Pass	Pass
Resistance to impact	BS EN 12691	mm	>MLV	200	200	200
Durability (artificial ageing)	BS EN 1296 and EN 1928	-	Pass/Fail	Pass	Pass	Pass
Durability chemical resistance	BS EN 1847	-	Pass/Fail	Pass	Pass	Pass
Resistance to tearing (nail shank) MD	BS EN 12310-1	N	MLV	140	175	270
Resistance to tearing (nail shank) TD	BS EN 12310-1	N	MLV	140	175	270
Water vapour transmission - resistance	BS EN 1931	MNs/g	MDV	586	682	1390
Water vapour	BS EN 1931	g/m <sup>2</sup> /d	MDV	0.36	0.32	0.16

## Visqueen DPM

transmission - permeability						
Visible defects	BS EN 1850 -2	-	Pass/Fail	Pass	Pass	Pass
Width	BS EN 1848-2	m	-2.5%/+2.5%	4m	4m	4m
Length	BS EN 1848-2	m	-10%/+10%	25	25	12.5

### Health and safety information

Refer to Visqueen DPM material safety datasheet (SDS).

### About Visqueen

Visqueen is a leading provider of construction membrane technologies and design-based solutions for ground gas, structural waterproofing, damp proofing and fire protection.

We offer complete support at every stage of the specification, including the supply chain process. As the UK's principal technical authority, we are best placed to ensure that the principal designer and contractor specify the most technically suited, durable, and competitive solution to guarantee their project is protected for the lifetime of the building.

Visqueen is at the forefront of advanced membrane technology and innovation in the construction industry, earning the trust and loyalty of specifiers throughout the UK and Europe.

For more information, visit [visqueen.com](http://visqueen.com) or contact our sales office at [+44 \(0\) 333 202 6800](tel:+44(0)3332026800) or [enquiries@visqueen.com](mailto:enquiries@visqueen.com)

### Complete Range, Complete Solution



Passive Fire Protection



Gas Protection



Damp Proof Membrane



Air and Vapour Control



Stormwater



Damp Proof Course



Temporary Protection

### Visqueen Technical Support

Visqueen offer a comprehensive full nationwide technical support. Our team of CSSW qualified technical support managers provide on site design-based solutions for specifiers, contractors and builders merchants, and will ensure that from design stage to installation the project is fully risk assessed and the specification is approved by all stakeholders.

Our Technical Office, can design, prepare and manage CAD detailing, together with assisting in quantity take offs, while offering advice on technical installations and product selection.

### Competency & Design

Visqueen promotes competency in building design by ensuring that its technical team possesses the necessary skills, knowledge, experience, and ethical practices. The company adopts the "golden thread of information," ensuring all project data is digitally secure and accessible throughout a building's lifecycle. This approach aligns with the Building Safety Act and aims to foster accountability and compliance with evolving regulations, providing clients with confidence in the safety and reliability of their projects.

### Visqueen CPD Seminars

Visqueen's CPD Seminars offer insights into Building Regulations, Standards, and industry guidance related to damp proofing, hazardous ground gas protection, and structural waterproofing. These one-hour seminars are tailored for construction design professionals and delivered by our Technical Support Managers. Visit our website to book a free CPD.

### Visqueen Contract Design Services

Visqueen Contract Design Services offers a bespoke design service led by our team of Certified Surveyors in Structural Waterproofing (CSSW), providing experienced and specialised waterproofing design expertise for complex projects. We provide comprehensive support throughout the entire project, ensuring that all work meets

## Visqueen DPM

the requirements of warranty providers and adheres to the highest standards of quality, reliability and current legislation.

---

## Visqueen Training Academy

Based at our Derbyshire facility, the Visqueen Training Academy offers a variety of training programs across the UK. These include one-day product awareness sessions for distributors and builders' merchants, and intensive two-day courses for hands-on product installation training. Contact us for more information.

---