

Report No.: 061583-1-a

Receipt date: July 26th of 2016
Test end date: August 22th of 2016
Report emission date: September 1st of 2016

Page 1 of 2

Client: INDUSTRIAS JUNO, S.A.
Contact person: Luis Gil
Address: Barrio Saconi, 10
Town: 48950 ERANDIO (Bizkaia)

REFERENCE: Dynapok al agua

STANDARD	TITLE	SAMPLE	AVERAGE ADDRESS 1	AVERAGE OPPOSITE DIRECTION	AVERAGE SAMPLE	RESULT WET (USRV)	CLASIFICACIÓN SEGÚN EL CTE
⁽¹⁾ UNE-ENV 12633:2003 Annex A	Method of determination of unpolished and polished slip/skid resistance value	1	86	86	86	85	Class 3 $R_d > 45$ (See tables I and II)
		2	80	80	80		
		3	86	87	87		
		4	87	86	86		

USRV: unpolished skid resistance value.

⁽¹⁾ This standard is cancelled, but is awaiting the publication of the standard that replaces.

Table I – Classification of soils according to their slipperiness

Slip resistance value R_d	Class
$R_d \leq 15$	0
$15 < R_d \leq 35$	1
$35 < R_d \leq 45$	2
$R_d > 45$	3

Report No.: 061583-1-a		Receipt date: July 26th of 2016 Test end date: August 22th of 2016 Report emission date: September 1st of 2016
		Page 2 of 2
Client:	INDUSTRIAS JUNO, S.A.	
Contact person:	Luis Gil	
Address:	Barrio Saconi, 10	
Town:	48950 ERANDIO (Bizkaia)	

Table II – Class required of soils according to their location

Location and soil characteristics	Class
Interior dry areas	
- Surfaces with a slope less than 6%	1
- Surfaces with a slope equal to or greater than 6% and stairs	2
Interior wet areas such as entrances to buildings from outer space (1), covered terraces, changing rooms, showers, bathrooms, toilets, kitchens, etc..	
- Surfaces with a slope less than 6%	2
- Surfaces with a slope equal to or greater than 6% and stairs	3
Outdoor areas. Pools ⁽²⁾ . Showers.	3
⁽¹⁾ Except in the case of direct access to restricted areas.	
⁽²⁾ In areas planned for barefoot users and at the bottom of the vessels, in areas where the depth does not exceed 1.50 m.	

- * In case of a lawsuit, the original Spanish version shall be taken as reference.
- * The results of this report concern only and exclusively to the material tested.
- * The complete information related to the required tests is at client's disposal on request.
- * This report may not be reproduced without the express authorisation of FUNDACIÓN TECNALIA R&I, except where done so in its entirety.