

HIGH GLOSS

Dulux Trade High Gloss is a solvent-based formulation which offers excellent flow, giving surfaces a tough, durable high gloss finish.

KEY BENEFITS

- Tough, Durable Finish
- Excellent Flow
- Coverage up to 18m² Per Litre

PRODUCT INFORMATION

Typical Use

Suitable for use on interior and exterior wood and metal surfaces.

Pack Size

1L, 2.5L and 5L.

Colour Range

See appropriate **Dulux Trade** colour literature or visit duluxtrade.co.uk.

Film Properties

Chemical Resistance: Resistant to mild chemical fume attack, but where there is heavy attack, such as actual contact with chemicals, specialist paint systems may be required (contact the **AkzoNobel** Technical Advice Centre).

Heat Resistance: Generally resistant to heat up to 90°C, but some discolouration of light colours may occur at elevated temperatures.

Water Resistance: Resistant to the levels of atmospheric humidity present in normal interior and exterior environments and will withstand repeated washing. Not suitable for immersed surfaces or where there is very heavy and prolonged condensation.

Film Thickness

Film thickness will be dependent on the coverage achieved.

Wet: 50 microns

Dry: 25 microns.

Composition (nominal)

Pigment: Lightfast Pigments.

Binder: Alkyd.

Solvent: White Spirit.

Volume Solids

White: 63% (nominal). Other colours will vary.

SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry), and free from all defective or poorly adhering material, dirt, grease and wax. New or bare surfaces should be primed with an appropriate **Dulux Trade** primer. Treat any knots in wood with an appropriate knotting solution.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Any surface defects should be filled with the appropriate **Polycell Trade Polyfilla**.

SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. Apply 1 coat of the appropriate coloured **Dulux Trade** Undercoat, followed by 1 or 2 coats of **Dulux Trade High Gloss**. When a fast drying system is required for new work, **Dulux Trade Quick Dry Wood Primer Undercoat** (available in white only) can be used as an alternative.

Allow a minimum of 6 hours for the undercoat to dry before applying the gloss finish. Where a second coat of **Dulux Trade High Gloss** is required, allow a minimum of 16 hours between coats.

For improved obliteration on rough or textured surfaces, or when using special process colours (see appropriate **Dulux Trade** colour literature), 2 coats of **Dulux Trade High Gloss** will be required in order to achieve full opacity.

NOTE: Whilst leading-edge technology has been used in the development of this product, the nature of white solvent-based paints means that they will all discolour over time. The rate of discolouration is faster on areas with no or low natural or UV light. For longer-lasting whiteness, we recommend the use of a water-based formulation such as **Dulux Trade Quick Dry Gloss**.

HIGH GLOSS

For best colour consistency, purchase sufficient tinted paint for each job including touch in at one time from the same source.

APPLICATION METHOD

Brush or roller only. For Health & Safety reasons relating to all solvent-based paints, spray application is not recommended.

As with other solvent-based paints, do not apply in temperatures below 5°C (as recommended by British Standard BS 6150).

Practical Coverage

On smooth surfaces of average porosity, a guide to the practical coverage that can be achieved is up to 18m² per litre.

Spray Recommendations

This product should not be sprayed.

Drying Times

Single coat at standard thickness:

Touch Dry: 4-6 hours.

Recoat: 16-24 hours.

FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:0333 222 70 70).

Always read full Health, Safety & Environmental Information on can before use.

Safety datasheet (SDS 403) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting duluxtrade.co.uk.

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.

Cleaning Up

After use, remove as much product as possible from equipment before cleaning with brush cleaner.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at duluxtrade.co.uk/pp.

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/d): 300g/l (2010). This product contains max. 300g/l VOC. VOC content: High (25-50%).